

PRODUCT DATA

3 03 35 00 **Concrete Finishing****MASTERPLATE® 200****Metallic-aggregate colored dry-shake surface hardener****Description**

Masterplate® 200 surface hardener is an iron-armored, ready-to-use cementitious dry-shake floor hardener. It utilizes specially treated, sized, and graded metallic aggregate. When evenly distributed and finished over freshly leveled and floated concrete, the aggregate improves wear and impact resistance for industrial concrete floors.

Yield

Primarily for wear resistance:
1.0 - 3.0 lbs/ft² (4.9 - 14.7 kg/m²).

Primarily for color: 1.8 - 3.0 lbs/ft²
(8.8 - 14.7 kg/m²).

Consult your BASF representative for specific recommendations.

Packaging

55 lb (25 kg) multi-wall bags

Color

Available in colors, including energy-efficient light-reflective formulations.

Shelf Life

18 months when properly stored

Storage

Store in unopened packaging in a clean, dry environment protected from sunlight at 50 to 90° F (10 to 32° C).

Features

- Light-reflective formulations
- Increased abrasion resistance
- Versatile finishes
- Greater impact resistance than plain concrete or mineral aggregates
- Strictly controlled and specially treated, and graded iron aggregate
- Creates a high-density surface

- Color options available

Benefits

- Reduce energy costs and lighting requirements
- Up to 4 times greater than mineral aggregates and 8 times greater than concrete
- Ranges from smooth to textured
- Protects slab surfaces and joint edges
- Provides uniformity and consistent finishing sized, characteristics
- Easy to clean and maintain; resists liquid penetration; reduces wear on the wheels of material-handling equipment
- Including energy-saving light-reflective formulations

Where to Use

APPLICATION

- Where hard composition or steel wheels on equipment are commonly used
- Airplane hangars (light-reflective formulation)
- Electronic assembly plants (light-reflective formulation)
- Manufacturing plants
- Warehouses and distribution centers
- Warehouses AGV aisles
- Shipping and receiving areas
- Maintenance facilities

SUBSTRATE

- Over freshly leveled and floated concrete

How to Apply**Surface Preparation**

1. Pump, place, or otherwise convey the base concrete at a slump not in excess of 5" (127 mm) for a slab on grade. (Please contact your local BASF representative for special information on suspended-slab application.) After the concrete has been placed, immediately screed, then bullfloat or highway straightedge the surface.
2. Do not apply the dry shake into the bleed water. If excessive bleed water is present, remove standing water by dragging a hose across the surface, using a squeegee or other approved method.
3. Early moisture loss and rapid setting around the perimeter of the slab are typical; monitor the slab closely for proper timing of the floating.

Application

1. If more than 1.0 lb/ft² (4.9 kg/m²) of total shake will be applied, apply the material in 2 or more applications. Apply and integrate one-half to two-thirds of the total amount on the first application and the remaining portion(s) on the subsequent application(s). Do not apply more than 1.0 lb/ft² (4.9 kg/m²) in 1 pass. An automatic spreader is the most efficient, economical, and precise method of applying a dry shake.
2. Allow the first application to absorb moisture, then reprofile the surface of the slab with an 8 – 10 ft wooden bullfloat or wood-laminate modified highway straightedge perpendicular to the direction on the screeding. (A wooden bullfloat is preferable because it tends to open the slab rather than close it off, possibly trapping water under the dry-shake layer. To maintain flatness, avoid shaking the bullfloat handle.)
3. When the slab can support the weight of a person without leaving more than a 1/8 – 1/4" depression, float the surface with a floating machine equipped with clip-on float blades. Hand float the edges with wood floats or darbies. Reprofile in both directions using the modified highway straightedge to achieve desired flatness.
4. Without delay, evenly apply the remaining portion of the product. Float the surface again with clip-on float shoes. Reprofile, if needed. If desired, pan float, followed by finish troweling.

NOTE: Do not use pan floats to incorporate the dry shake into the base concrete; however, they may be used for final floating to achieve flatter floors. Hand float edges with wood or laminated canvas-resin floats or darbies; magnesium floats can lead to discoloration.

Troweling

1. When appropriate conduct 2 – 3 mechanical trowelings. Leave the prepared slab untouched until the surface has lost its sheen and can support the weight of a finisher and a finishing machine. At this point conduct the first troweling of the surface.
2. On the first application keep trowel blades as flat as possible without digging into the surface.
3. As the surface tightens further, the trowel blades may be gradually raised to produce the desired surface. Remove all marks and pinholes in the final slightly raised trowel application. Do not burnish colored dry-shake floors.

NOTE: All moisture used to incorporate dry-shake material must come from within the slab. UNDER NO CIRCUMSTANCES SHOULD WATER BE APPLIED TO AID IN THE INCORPORATION OF THE DRY SHAKE. Under severe or rapid drying conditions, Confilm® evaporation reducer, or other approved materials, may be mist sprayed onto the dry shake to prevent rapid-moisture loss. MISUSE OF THESE MATERIALS CAN COMPROMISE COLOR AND PERFORMANCE OF THE DRY SHAKE.

Curing

1. At the completion of final troweling and when the surface will not be marred, apply an approved membrane curing compound.
2. After drying, protect hardened surface by covering it with a scuff-proof, non-staining builder paper.
3. Keep floors covered and free of traffic and loads for a minimum of 10 days after completion.
4. Maintain ambient temperature at 50° F (10° C) or above during the curing period.
5. Do not water or moist cure or cure with polyethylene.
6. For VOC-compliance on colored floors, contact your local BASF representative for curing recommendations.

Joints

OPTION 1: SEMI-RIGID EPOXY JOINT FILLER

1. After a minimum of 90 days*, apply a semi-rigid epoxy joint filler (e.g., Masterfill® 300i) in all non-dynamic control and saw-cut construction joints. Place the joint filler in compliance with manufacturer's instructions.

*Please refer to ACI 302R-96, Chapter 9.10. Delay the installation of the joint filler as long as possible to allow the slab(s) to adequately cure. Proper curing will reduce the amount of separation between the slab and the joint filler.

OPTION 2: IRON-ARMORED JOINTS

1. Remove the concrete at the joints while it is still fresh. Remove it to a depth of 1/2" (13 mm) at the joint line and taper it back to the surface level over a width of 4" (102 mm).
2. Mix the Masterplate® 200 surface hardener with enough water to produce a stiff mortar. Hand float the area where the concrete has been removed, working up sufficient paste at the surface to ensure an integral bond.
3. Immediately place the Masterplate® 200 mortar into the prepared joint, then rescreed the area to level. Use 4.50 lbs (2.0 kg) per lineal foot, which is 2.25 lbs (1.0 kg) per foot for each side of the joint.

For Best Performance

- Masterplate® 200 colored floors require extra care during construction. The newly constructed floor must be protected from staining and damage until the structure goes into service. Many factors, including jobsite conditions and applicator methods, can affect the final shade, color, and appearance of a colored concrete floor.
- Consult appropriate sections of ACI Committee Report 302 "Guide for Concrete Floor and Slab Construction" for monolithic colored dry-shake finishes.
- Store materials in a dry place; do not use material if the packaging is damaged.
- Do not install over concrete containing calcium chloride or concrete containing aggregate that has been saturated with salt water.
- Do not install over concrete containing more than 3% air content as measured by ASTM C 138, ASTM C 173, or ASTM C 231.
- If any blistering occurs during the finishing operation, flatten trowel blades immediately. Refloat to "open" the floor and rework blistered areas with hand floats. Delay raised troweling until no blisters occur.
- Wood or composition-fiber hand floats are recommended for Masterplate® 200 installations.
- Use only high-pH terrazzo solutions to clean Masterplate® floors.
- Do not use in areas where floor surfaces will be routinely exposed to standing water.
- Not recommended for fire-station applications.
- Arrange to have a pre-job conference with your local BASF representative to discuss all aspects of the dry-shake application. Give a copy of the proposed mix design to your BASF representative. Cement, aggregate size, aggregate gradation, admixtures, and other factors can all affect set time and the ability of the slab to incorporate the dry shake.
- Before starting the application, contractors should install a 10 by 10 ft. (3 by 3 m) test application using actual jobsite products and methods for the approval of the owner and architect.
- This product data sheet describes how to effectively apply Masterplate® 200 dry-shake surface hardener. However, ideal results of these, or any construction product, are highly dependent upon applicator experience, ambient conditions, proper equipment, labor and installation procedures, proper curing, and other factors.

- Protect this product from weather during installation. Place concrete floors under a roof, if at all possible. Job conditions that influence surface drying and setting time of the concrete also affect the timing of the hardener application, the finishing procedures, and the reflectivity of the slab.
- Proper ventilation must be provided. Unvented flue and exhaust gasses from heaters and equipment can cause a carbonated floor surface. This results in a weak and potentially dusting surface.
- Proper timing is essential for successful installation of this product. Follow the given procedures at the recommended time.
- To ensure consistent, proper coverage throughout the installation, position bags of material around the perimeter of the slab.
- Make certain the most current versions of product data sheet and MSDS are being used; call Customer Service (1-800-433-9517) to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

Health and Safety

MASTERPLATE® 200

WARNING!

Masterplate® 200 contains silica, crystalline quartz; portland cement; iron oxide; titanium dioxide; anhydrite; chromium oxide; iron oxide; limestone; gypsum; magnesium oxide; silicon dioxide.

Risks

Product is alkaline on contact with water and may cause injury to skin or eyes. Ingestion or inhalation of dust may cause irritation. Contains small amount of free respirable quartz which has been listed as a suspected human carcinogen by NTP and IARC. Repeated or prolonged overexposure to free respirable quartz may cause silicosis or other serious and delayed lung injury.

Precautions

Avoid contact with skin, eyes and clothing. Prevent inhalation of dust. Wash thoroughly after handling. Keep container closed when not in use. DO NOT take internally. Use only with adequate ventilation. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable Federal, state and local regulations.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

Waste Disposal Method

This product when discarded or disposed of, is not listed as a hazardous waste in federal regulations. Dispose of in a landfill in accordance with local regulations.

For additional information on personal protective equipment, first aid, and emergency procedures, refer to the product Material Safety Data Sheet (MSDS) on the job site or contact the company at the address or phone numbers given below.

Proposition 65

This product does not contain materials listed by the state of California as known to cause cancer, birth defects, or reproductive harm.

VOC Content

This product contains 0 lbs/gal or 0 g/L.

**For medical emergencies only,
call ChemTrec (1-800-424-9300).**

**BASF Construction Chemicals, LLC –
Building Systems**

889 Valley Park Drive
Shakopee, MN, 55379

www.BuildingSystems.BASF.com

Customer Service 800-433-9517

Technical Service 800-243-6739



LIMITED WARRANTY NOTICE: Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

For professional use only. Not for sale to or use by the general public.

Form No. 1019592 7/07

Printed on recycled paper including 10% post-consumer fiber.

© 2007 BASF

Printed in U.S.A.